



## Swift® col 9050

- Тип клея** Клей на основе растворителя.
- Преимущества** Склеивание при помощи Swift® col 9050 характеризуется хорошей термо устойчивостью приблизительно при 100°C, в зависимости от механического воздействия.
- Типичное применение** Swift® col 9050 используется для склеивания термически податливого пластикового ламината при постформинге и при глубоком вакуумном нанесении тяжелой ПВХ пленки. Клей может дополнительно использоваться для склеивания ламинирующих листов, пластиковой пленки и листов включая листы металла к дереву, материалы на основе дерева и тяжелые пены (за исключением пенополистирола). Наносится оборудованием для окутывания или распылителем. Swift® col 9050 также подходит для склеивания спортивных матов.
- Подходящие материалы** Пластик, металл, материалы на основе едерева и тяжелые пены.

### Типичные свойства

Характеристика	Величина
Основа	Полихлоропрен
Цвет	красный
Вязкость	(Brookfield) Ca. 300 mPas*
Плотность	Ca. 0,83 g/cm <sup>3</sup>
Хранение	12 месяцев



# H.B. Fuller



## TECHNICAL DATA SHEET

<b>Нанесение Инструкции</b>	<b>Метод нанесения</b> : Окутыватель или распылитель <b>Покрытие</b> 180 - 200 g/m <sup>2</sup> <b>Время высыхания</b> 2 – 5 мин при нанесении распылителем, 5 – 20 мин при нанесении окутывателем <b>Время контакта</b> 40 – 50 мин
<b>Очистка</b>	Свяжитесь, пожалуйста, с офисом продаж в Вашем регионе
<b>Упаковка</b>	Свяжитесь, пожалуйста, с офисом продаж в Вашем регионе
<b>Условия хранения</b>	В оригинальной плотно закрытой упаковке в защищенном от солнца, пыли, влаги и высоких температур месте. Чистые и сухие условия хранения при температуре ниже 10°C.
<b>Утилизация</b>	Пожалуйста, ознакомьтесь с Паспортом безопасности.
<b>Меры предосторожности</b>	Пожалуйста, ознакомьтесь с Паспортом безопасности.

**Our Focus is Clear. Perfecting Adhesives.**

**IMPORTANT:** The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.



## H.B. Fuller

**H.B. Fuller Company**

info-europe@hbfuller.com  
www.hbfuller.com/  
eimea/contact-us